Enhancing energy storage in aluminum foil capacitors with calcium zirconate as dielectric material

Sunday Chimezie Anyaora*, Solomon Chuka Nwigbo, Christian Emeka Okafor, Victor Mmerichukwu Mbachu

Nnamdi Azikiwe University, PMB 5025, Awka, Anambra State, Nigeria
*Corresponding author, email: sc.anyaora@unizik.edu.ng

Article history
Submitted: 23 November 2025
Revised: 25 January 2026
Accepted: 30 January 2026
Published: 3 February 2026

Keywords
Aluminum foil capacitors
Calcium zirconate
Capacitor performance
Dielectric materials
Energy storage

Abstract
The rapid growth of electronic systems has increased the demand for high-energy-density capacitors with improved reliability and thermal stability. Conventional aluminum oxide dielectrics limit the energy storage performance of aluminum-foil capacitors, which are widely used in power electronics, automotive systems, and consumer devices. This study presents a systematic narrative review focusing on the potential of calcium zirconate as an alternative dielectric material to enhance the energy storage capacity of aluminum-foil capacitors. Relevant peer-reviewed literature published between 2010 and 2025 was retrieved from Scopus, Web of Science, ScienceDirect, IEEE Xplore, and Google Scholar using targeted search terms related to capacitor types, dielectric materials, and performance characteristics. Articles were screened based on title, abstract, and full text to ensure relevance and data quality. A thematic analysis was employed to identify current trends, research gaps, and opportunities for integrating calcium zirconate into aluminum-foil capacitor systems. The review examines capacitor classifications, dielectric materials, and distinctions between electrostatic and electrochemical capacitors, with particular emphasis on aluminum-foil technologies. Key performance indicators, including capacitance, equivalent series resistance (ESR), reliability, and thermal behavior, are discussed alongside metallurgical, structural, and manufacturing considerations. Recent technological advancements and application prospects are also highlighted. Overall, the incorporation of calcium zirconate as a dielectric shows strong potential to improve energy density, thermal stability, and long-term reliability, offering a promising pathway for next-generation electronic capacitor applications.

1. Introduction

The aluminum foil capacitors are widely used in electronic systems due to their low cost, high reliability and ability to be produced at a large scale. They play a decisive role in the conditioning of power, signal coupling and storing energy in consumer electronics, automotive systems and industries. However, despite their benefits, traditional electrolytic capacitors made of aluminum are limited to a small storage capacity of energy, thus limiting their performance in the modern high-power and miniaturized electronic devices [1]. This constraint has been further accentuated by the increasing demand to have small, energy-saving, and high-performance electronic components. Dielectric material is the most important factor that determines the energy storage capability of aluminum foil capacitors. Conventional capacitors are based on the use of aluminum oxide as dielectric layer; it is a stable material, however, with relatively low dielectric constant that limits the storage of charge per unit volume [2]. As a result, a growing research attention is now being given the development of superior dielectric materials capable of increasing the capacitance without reducing thermal stability, electrical insulation and long-term reliability. The challenge then is to find dielectric materials with high permittivity, low dielectric loss with compatibility to aluminum substrates.

Calcium zirconate ($CaZrO_3$) has been proposed as a candidate dielectric material to combat this issue. Calcium zirconate is a perovskite oxide ceramic, which exhibits excellent dielectric characteristics, such as a relatively high dielectric constant, low leakage current, and high thermal and chemical stability [3]. The features make it applicable in high energy density applications, especially where high standard dielectrics would be prone to deterioration. Introduction of calcium zirconate in the aluminum foil capacitors provides a way of improving the energy storage capacity significantly yet maintaining structural integrity and operational performance. In terms of materials- engineering, calcium zirconate also increases energy storage by increasing the effective dielectric constant of the capacitor system. Under the relationship of capacitance, the greater the dielectric constant, the better charge storage. In addition, calcium zirconate is highly resistant to dielectric breakdown, which allows capacitors to work more and more at increased voltages [4]. This multiplicity of high permittivity and breakdown strength is needed in achieving increased energy density in small capacitor designs.

Capacitor is one such energy storage device that stores electrical charge between two conducting plates also known as the electrodes, separated by a non-conductive substance known as the dielectric. Application of

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

a potential difference across the two terminals results into an electric field within the dielectric, which causes opposite polarity charges upon the plates. This energy can subsequently be discharged, and the device can provide power and to process signals. Elementary components of electronic equipment include capacitors, which are typically used in buffering, filtering, decoupling, and power-factor correction of energy. They can work based on the principles of electrostatics, namely the ability of the dielectric substance to support an electric field without considerable conduction [5]. The capacitance value varies with the area of the plates, the distance between them and the dielectric constant of the insulating material. They are applied in the small-scale microelectronics circuits and large-scale power-transmission systems, where the high-speed response and stable energy supply become prerequisite [6].

Electrolytic capacitors are also known to have a large ratio of capacitance to volume making them irreplaceable in power electronics, particularly in filtering, buffering, and smoothing circuits of rectifiers. They are normally made with the use of an aluminum or tantalum foil, paper-based spacer, infused with electrolyte, and a secondary foil that is able to store high energy per unit volume, though at the cost of lower voltage ratings, and shorter life compared to ceramic or film ones [7]. Electrolytic capacitors in the energy system are used to help stabilize voltage and power flow as well as reduce ripples and transients that would otherwise destroy delicate electronic components. They are especially pressing in converters and inverters of DC to DC and systems associated with renewable energy, including solar inverters and battery-management systems [8], [9]. However, chronic difficulties on thermal instability and frequency response inhibit their use in the high temperature or high frequency domain. Attempts to raise the energy density and thermal stability through dielectric layer quality improvement and electrode surface treatment are mostly in laboratory testing [10]. In addition, although their ability to dominate industry remains due to their low costs and ubiquity, electrolytic capacitors are rarely designed to be efficient with regard to sophisticated energy storage.

Despite its promising dielectric properties, the integration of calcium zirconate into aluminum foil capacitors is constrained by several technical and systemic challenges. Achieving film uniformity and strong interfacial bonding with aluminum substrates remains difficult, often increasing fabrication complexity and cost [11]. These challenges mirror broader implementation problems observed in material and environmental systems, where process inconsistency undermines performance outcomes [12]. Scholars have emphasized that advanced fabrication techniques such as sol–gel processing and chemical vapor deposition are essential for minimizing defects and enhancing structural reliability [11]. Similar to sustainability-driven infrastructure and green maintenance initiatives, successful material deployment depends on balancing innovation with cost efficiency and technical capacity [13]. Furthermore, contextual and risk-aware approaches are critical in managing complex systems, whether in advanced materials engineering or climate communication and governance frameworks [14], [15]. Without such integrated strategies, technological adoption remains fragmented and unsustainable [16].

The growing need to explore sustainable energy storage in aluminum foil capacitors incorporating calcium zirconate as a dielectric material reflects a widening gap between traditional capacitor technologies and the performance demands of modern electronic systems. Much like institutional frameworks that struggle to keep pace with governance and service delivery expectations, outdated capacitor materials are increasingly inadequate for high-efficiency applications [17]. The push for advanced dielectrics mirrors calls for reform, adaptability, and accountability within public systems, where innovation is necessary for relevance and sustainability [18], [19]. As with regulatory structures that must evolve to address contemporary challenges, energy storage technologies require improved material design to ensure stability, efficiency, and long-term functionality [20]. Sustainable capacitor development therefore aligns with broader systemic transitions toward resilience and optimized performance [21]. Aluminum foil capacitors are appreciated due to their affordableness and robustness, but their energy-storage is inherently limited by the fact that the common dielectric constant of the popular aluminum-oxide dielectric film is low [4]. This is limiting efficiency and design flexibility as electronic devices continue to be smaller and more power-intensive.

Recent researchers have studied high-k dielectric-based ceramics in order to improve capacitor functionality, but most studies have utilized materials like barium titanite and titanium dioxide, which often have high dielectric loss, thermal variation, or incompatibility with aluminum substrates [22]. Therefore, there is still a research gap in finding alternative dielectric materials that would provide high permittivity, thermal stability and low leakage current at the same time. Although calcium zirconate has favourable dielectric and structural properties, it has not been extensively exploited in the aluminum-foil capacitor. Furthermore, the available literature has focused on bulk ceramic capacitors, and minimal efforts have been given on thin-film or composite dielectric integration on aluminum foils that can be fabricated in large quantities [23]. This gives the urgency in a dedicated study into calcium zirconate-based dielectrics that are specifically designed to work with aluminum-foil capacitors, thus, contributing to the development of high-energy-density, stable, and scalable capacitor technologies.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

2. Method

The present research is based on the systematic narrative review methodology, which interrogates the body of literature on the improvement of energy storage in aluminum foil capacitors with special attention to the creation and use of calcium zirconate as a dielectric material. The review does not attempt to produce any new empirical data instead of synthesizing theoretical, experimental, and applied literature in the fields of materials science, electrical engineering, and capacitor manufacturing. Curated Boolean search strings using phrases like, but not limited to, aluminum-foil capacitors, dielectric materials, and calcium zirconate and perovskite oxides and energy density in capacitors and electrolytic capacitor performance were used to search academic databases, including Scopus, Web of Science, ScienceDirect, IEEE Xplore, and Google Scholar. It was limited to peer-reviewed journal articles, conference proceedings, and authoritative review papers most of which were published between 2010 and 2025, thus ensuring relevancy in the foundation and relevancy in the present.

The inclusion criteria were that the study must have covered capacitor classification, dielectric behaviour, and processing of aluminum foil, the difference between electrostatic and electrochemical energy storage mechanisms, and the performance metrics such as capacitance, equivalent series resistance, leakage current, dielectric strength and thermal stability. Research papers were eliminated that did not specifically concern capacitor technology, were concerned with other inapplicable ceramic systems, or lacked adequate methodological or performance information. The two-stage screening approach was used: first, the relevance of titles and abstracts was evaluated; next, full-text analysis was conducted to find out the essential information about material properties, fabrication methods, structural attributes, and performance results.

They were used to extract data based on thematic categories in accordance with the structure of the reviews, and included capacitor types, dielectric materials, properties of calcium zirconate, manufacturing process, performance measurements, technological developments and applications. The obtained results underwent qualitative analysis to identify trends, consistency, and gaps in literature. Special consideration was given to those areas in which calcium zirconate had been a little neglected or mentioned indirectly in connection with aluminum-foil capacitors. Instead of statistical aggregation to synthesize the concept, the synthesis used a conceptual integration strategy, thus allowing a critical interpretation of the way calcium zirconate could strengthen the energy storage capacity of established capacitor architecture.

3. Results and Discussion

3.1. Classification of Capacitor

3.1.1. Ceramic Capacitors

Ceramic capacitors are made of a ceramic material that functions as a dielectric and are typically implemented for high-frequency operating performance and stable temperature uses (Figure 1). They are non-polarized, thus can be placed in a circuit without regard to polarity, and are found to be widespread usage for signal filtering, RF circuits, and bypass circuits. Because they are small in size, together with low cost, they are found to be of value for mass production, but are limited for lower values of capacitance compared to others. Their features are varied further depending on the value of the ceramic temperature coefficient that can be segregated into types like Class I (stable) and Class II (larger capacitance but less stable) [10].



(Source: https://support.google.com/legal/answer/3463239?hl=en-NG)

Figure 1. Ceramic Capacitors

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

3.1.2. Film Capacitors

Film capacitors are constructed using plastic film as the dielectric material. They offer excellent insulation resistance, low dielectric absorption, and high stability across temperature and frequency ranges (Figure 2). These properties make them suitable for audio, power conditioning, and pulse applications. Film capacitors are often used in environments where precise capacitance retention is required over time and under varying operational conditions [7].



(Source: www.wikipedia.com)

Figure 2. Film Capacitors

3.1.3. Electrolytic Capacitors

Electrolytic capacitors use an electrolyte impregnated material as their dielectric, and they are normally built using an anode of aluminum or tantalum. Being polarized devices they require correct polarity connection in a circuit. Their major benefit is their capability to provide very large capacitance values whilst fitting in a relatively small envelope, and they have become essential to both energy storage, filtering and decoupling in power supply systems. This is, however, usually limited by reduced permissible voltage ratings and reduced operational lifetimes, mainly caused by the evaporation of electrolytes or by material degradation [8].

3.1.4. Supercapacitors and Electrochemical Capacitors.

Supercapacitors or ultracapacitors are a specific type that combines the properties of the traditional capacitor with the properties of an electrochemical battery (Figure 3). They reach capacitances that are significantly high due to the ability of the electric double layers to store charge or due to the pseudo capacitance mechanisms. They are thus used in systems where charge-discharge cycles are in short order, like in regenerative braking, uninterruptible power supplies, and memory backup circuits [24]. They have a lower voltage rating and energy density than batteries, despite having much higher energy storage capacities than conventional capacitors.



(Source: www.scienceDirect Topics)

Figure 3. Electrochemical Capacitor

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

3.1.5. Variable Capacitors

Variable capacitors allow for adjustable capacitance, commonly used in tuning circuits like radio receivers. Their structure usually includes a set of movable plates whose overlap with fixed plates determines the capacitance. Though they are not common in modern miniaturized electronics, they remain relevant in specific analog and RF design applications [25]. Variable capacitors can be seen in Figure 4.



(Source: https://passive-components.eu/variable-capacitors/)

Figure 4. Variable Capacitor

3.1.6. Hybrid Capacitors

Hybrid capacitors attempt to bridge the performance gap between electrostatic and electrochemical types (Figure 5). These devices combine materials and structures from both categories to create capacitors that exhibit improved energy and power densities. They often involve asymmetric designs, where one electrode supports electrochemical storage and the other electrostatic storage. Such configurations are still under extensive research but offer considerable promise in applications that require balancing fast energy delivery with extended storage capacity [9].



(Source: https://industry.panasonic.eu/products/components/capacitors/hybrid-capacitors)

Figure 5. Hybrid Capacitor

3.2. Dielectric Materials

Dielectric materials are understood in capacitors work through the storage of electric field without being a conductor (Figure 6). Insulating materials are situated between plates of a capacitor and are implemented for the enhancement of the capacitance through storing more electric field lines for a given volume. Some of the most familiar dielectrics are ceramics, polymers, glass, paper, and more recently, nanostructured oxides such as HfO_2 and TiO_2 due to larger dielectric constants and thermally stable [7]. A capacitor's performance remains closely associated with the dielectric constant of a specific material, alongside its response of temperature and voltages. An effective dielectric must be able to accommodate high field strengths, possess minimum dielectric loss, alongside the capacity for resisting environmental degradation. As energy storage technology improves, so too interest remains in conventional dielectrics with carefully engineered nanostructures such engineered material possesses better breakdown voltages and polarization stability due to limited grain boundaries alongside larger interface area [9]. Dielectric breakdown due to electrical overstress remains a limiting factor, thus development of new material remains a central point for enhanced capacitor endurance alongside size diminution. Inclusion of high-k dielectric composites within energy storage capacitors brings new hope for realizing larger energy densities without adding bulk size, which remains vital for mobile alongside embedded system uses [10]. Consequently, selecting and implementing the correct dielectric material remains a vital aspect for realizing a capacitor's reliability alongside efficiency, particularly for energy uses of high demand.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577



(Source: https://byjus.com/physics/dielectric-properties/)
Figure 6. Dielectric materials

3.3. Calcium Zirconate

Calcium zirconate ($CaZrO_3$) is an inorganic material that is a compound of calcium, zirconium and oxygen atoms which are arranged in a perovskite-type structure. It has attracted significant interest due to its extremely high temperature stability, significantly low dielectric loss, and moderate dielectric constant, which makes it very useful as a dielectric medium in energy-storing devices like capacitors (Figure 7). The structure of perovskite gives calcium zirconate a strong structural integrity when subjected to electrical and thermal stress, which enables a dielectric layer of a capacitor to keep operating consistently and with longer time intervals [26]. Calcium zirconate has overcome the intrinsically higher dielectric breakdown resistance and polarization fatigue resilience characteristics of polymeric or conventional dielectric alumina than any other material. Its strong chemical bonding inhibits ionic mobility that as a result reduces leakage currents and enhances long term energy storage in capacitors. Therefore, calcium zirconate has become the subject of attention of the researches intended towards developing advanced dielectric systems with the aim of energy-efficient electronic devices and pulsed-power technologies [27].

Zircon (ZrSiO 4) is a mineral formed naturally, most often in sand deposits, and is the most commonly used raw material in the production of calcium zirconate. In order to make it usable as a ceramic material, a series of chemical and thermal processes are required to eliminate silica and other impurities that are present in the sand, and eventually produce purified zirconium oxide. This fine oxide is then combined with calcium oxide and the mixture is subjected to a high temperature reaction in the solid state - usually over 1200 0 C - to create calcium zirconate. The whole production cycle requires high attention to the temperature, residence time, and purity of materials to avoid the occurrence of unwanted phases or incomplete reactions. Empirical evidence suggests that the efficiency of this route is highly dependent on the purity of the starting material; the purity of the starting sources of zircon; as well as the homogeneity of the reactant mixture; any remaining traces of unrefined silicates or metallic impurities may undermine dielectric performance and mechanical integrity of the end product; that is, the final ceramic. To this end, careful refinement methods like calcification, sieving, and chemical leaching are the necessary preconditions before the application of calcium zirconate in capacitor technologies.



Source: www.nanorh.com.
Figure 7. Refined calcium Zirconate powder

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

In a dielectric application, calcium zirconate has a role that cannot be overlooked because it accumulates electrical energy between two conductive plates, which are normally made of foil metal. Its main purpose is to hold this stored energy until it is needed and then it can release it very fast and efficiently. The basis of this ability is the dielectric strength and permittivity of the material. Calcium zirconate offers greater stability and more uniform behaviour between low and high temperature, but cannot compete with other materials, like barium titanate, with the largest dielectric constant. As an example, research has shown that it has low dielectric losses and high insulation resistance at temperatures above 300 0 C [28]. These attributes make it specifically beneficial in the high-power use cases, where temperature control is infamously difficult. In most industrial applications, the equipment needs to run under load on a continuous basis, and the dielectric material cannot degrade or disintegrate over long periods. The strength of calcium zirconate in such environments renders it an attractive capacitor in these harsh environments.

The effectiveness of calcium zirconate depends on its structural and surface properties as well. Microstructural properties such as the grain size, porosity and secondary phase existence influence the behavior of the material under electrical load. Ceramics that have a dense, uniform distribution and fine granules normally have greater dielectric breakdown strength and reduced energy loss. To realize such a microstructure requires rigorous sintering and high-purity starting materials. Unless zircon is refined completely or the sintering temperature is correctly high, the resulting calcium zirconate can have voids, cracks, or glassy residue which undermine performance. A number of studies highlight the significance of grain-boundary control, which indicates that impurities are concentrated at these boundaries and reduce the breakdown resistance of the material used [29]. Therefore, the raw-to-final ceramic processing pathway should be carefully constructed to maintain dielectric integrity.

Researchers have also tried in the last few years to improve the performance of calcium zirconate by doping. Adding small traces of metal oxides (yttrium or magnesium) scientists can control growth mechanisms in grains or change the behavior of the material to electric fields. As an example, some dopants minimize dielectric loss, other dopants increase breakdown voltage, and some dopants enhance thermal stability. The adjustments are also useful especially when the material is to be adapted to a particular use such as capacitors in power inverter or signal conditioning circuits. Doping allows the engineers to optimize the behavior of calcium zirconate without undergoing any radical changes in the manufacturing process, hence maintaining low production costs. Such a high level of dielectric strength, thermal, or even mechanical toughness modulation makes calcium zirconate a versatile material with extensive use in modern electronics [30].

3.4. Distinction Between Electrostatic and Electrochemical Capacitors

Capacitors can be distinguished according to the mode of energy storage mechanism: either electrostatic or electrochemical. Electrostatic ones, which consist of ceramic, film, and others, can store energy based on charge separation of a dielectric material. These ones are of low energy density but of high-power density, rapid charge/discharge cycle, and of high reliability for long-lived operations [31]. These are best implemented for circuits where rapid delivery of power is desired with small dissipation, such as for high-frequency switching operations. Electrochemical capacitors that are more familiarly referred to now as supercapacitors or ultracapacitors, can store energy through the means of electrochemical double layers or pseudocapacitive effects. Electrochemical ones can achieve energy densities equivalent for batteries but are still able to retain the rapid charging advantage of conventional capacitors [24]. Nevertheless, they are characteristically limited by lower power density, yet with a higher cost due to the sophistication of the electrode materials, particularly the electrolytes. It is the nature of the dielectric medium that imposes a fundamental difference: while the electrostatic ones employ solid insulators, the electrochemical ones rely on mobility of ions from liquid or gel electrolytes. This structural approach difference creates ranges of fields of application electrostatic ones are chosen for precision devices, while a different generation of ones are chosen for energy-intensive applications such as regenerative braking service and hybrid electric devices. Both share limitations, but trends are towards eliminating the gap of performance through hybridized material science, philosophy of design, but inherently, these are still technically, functionally different[9], [31].

3.5. Aluminum Foil in Capacitor Design

Aluminum electrolytic capacitors consist of anode aluminum foil formed with aluminum oxide film on the surface to function as the dielectric (Figure 8). The cathode aluminum foil functions as a collector, and the liquid electrolyte functions as the real cathode. Aluminum foil is also known as a fundamental component in capacitor design, offering a unique combination of properties that enable efficient energy storage and release.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577



Source: https://www.indiamart.com/proddetail/capacitor-aluminum-foil-13341768948.html

Figure 8. Aluminum Capacitors foil

3.6. Metallurgical and Structural Properties

Aluminum foil used in capacitor construction is not a generic metal sheet; it is a high-purity alloy specifically engineered for dielectric film formation and high surface area retention. These are characteristically more than 99.99% pure aluminum to minimize chances of inclusions or impurities that might degrade the quality of the oxide layer or compromise the electrochemical stability [7]. These foils are subjected to a number of processing stages including cold rolling, intermediate annealing, and ultimate recrystallization, resulting in a grain structural balance that optimizes uniformity of anodization. Such a grain structure promotes regular dielectric film creation, accompanied by mechanical flexibility, which plays a vital role during the winding and assembly of capacitors [30]. Characteristic of these metallurgical treatments is the stimulation of a cube-textured grain orientation, which enhances adhesion of the films, accompanied by a minimization of current leakage paths.

The structural properties of aluminum foils are also of primary Importance for substrate capacitor performance. Grain boundaries, residual stress levels, and dislocation densities govern the creation of a uniform layer of oxide via anodization. The unbalanced deformation of foils or retention of strain energy may cause non-uniform distribution of dielectric layers, resulting in untrustworthy dielectric spots or pinholes [32]. Thermal processing therefore needs to be done accurately: Low-rate annealing reduces stress gradients and encourages desirable kinetics of recrystallization. The phenomena are carefully tracked using EBSD and XRD characterizations and they reveal direct proportions between grain orientation, planarity of substrate and dielectric reliability [33].

Materials-wise, substrate purity and aluminum substrate grain structure likewise determine corrosion resistance and electrochemical compatibility. Exposed to electrolytes during operating capacitors, low-alloy purity or unsatisfactorily recrystallized regions can be prone to pitting or intergranular corrosion that can compromise the integrity of the dielectric and capacity retention [34]. In modern processing lines, therefore, in-line systems of scanning are complemented with metallographic inspections for detection of unsatisfactory regions of foil and removal of these.

3.6.1. Aluminum Oxide as Dielectric: Preparation and Stability

Aluminum oxide (Al_2O_3) production for the dielectric layer is realized through anodization governed electrochemical oxidation of the aluminum in acid electrolytes. In the process, a dense, amorphous layer of the oxide is instantly generated on the substrate metal, which is to be the medium of the dielectric. This layer is inherently self-regenerating and strongly adhesive, a result of the barrier-type of the anodic film that forms through inward O^{2-} and outward Al^{3+} ion migration [35]. One of the major advantages of anodized aluminum oxide is that it can be accommodated on substrate surface topography, with a uniform coverage of the dielectric even on etched microstructures. Since the growing oxide builds up equally in dimensions, the layer possesses a high dielectric strength usually a value of more than 700 V/μm for thin films such that, the capacitor can be powered at high voltages without dielectric breakdown.

Anodized aluminum oxide's dielectric reliability depends heavily on processing variables such as ramp rate of the voltage, electrolytic type, and temperature. According to literature, slow ramp-up of the voltage during the anodization yields denser films with low pore numbers, giving better long-term resistance to the voltage and lower leakage current [36]. Moreover, stabilization treatments like hydration or sealing in a boiling bath of deionized water can change the external amorphous oxide to crystalline boehmite or gamma-alumina, enhancing the dielectric performance through defect sealing. Long-term, however, thermally induced relaxation coupled with electrolyte absorption results in deterioration of the dielectric, a situation that remains of interest to capacitor designers for expanding operational lifetimes under cyclical stress.

Another critical factor is oxide integrity under mechanical and thermal load. Thermal mismatch between the base of aluminum and the oxide film can cause cracking of the dielectric, particularly under high-voltage or pulsed loads. Due to the brittleness of the oxide and low level of fracture toughness, underlying foils must be

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

dimensionally stable without causing shear stress or strain localization [37]. Controlled doping of the oxide or the use of stabilizing additives is being researched to increase crack resistance.

3.6.2. Surface Area Enhancement via Etching

The electrochemical etching of an electrolyte foil makes it impossible to achieve optimal capacitor design because the capacitance of an aluminum electrolytic capacitor is fundamentally dependent on the surface area of the anode foil. Electrochemical etching produces a fine, three-dimensional microtopography: usually containing tunnel or pits-like voids that increase the number of oxide growth sites, thus increasing the overall capacitance [7]. Traditionally the etching process is performed in aqueous solutions of hydrochloric or nitric acid and the voltage and current carefully controlled. The orientation of the foil, the composition of the etchant and the length of time determine the resulting microtopography; preferably vertically aligned grains will produce etched channels that are uniform which will be used to reduce both impedance and leakage current.

Recent activities in etching control focus on laser-interference-patterned, powder-aided-etching, and voltage-modulated etching sequences, all oriented to the maximization of pore density and uniformity [30]. These methodologies allow the selective etch of particular crystallographic domains, which increases the yield of the etch and suppresses over-etching and localized thinning. Properly etched foil has a high aspect-ratio surface profile, and has little subsurface damage to the underlying metal; this morphology enables strong dielectric layer formation and reduces the equivalent series resistance (ESR) that is observed in the ultimate capacitor assembly. Moreover, it is also crucial that the etching should not attack grain boundaries or cause excessive undercutting because these two phenomena undermine the mechanical integrity of the foil and trigger an early termination of the work. 3D surface profile graph showing increased area post-etching can be seen in Figure 9.



(Source: https://www.researchgate.net/figure/3D-optical-surface-profiler-images-of-the-aluminum-surface-after-etching-in-a-1-M-b_fig1_287203449)

Figure 9. 3D surface profile graph showing increased area post-etching

Another consideration is the interaction between etched structures and dielectric formation. The oxide layer must conform to the etched contours without trapping voids or forming non-uniform thicknesses, as these would introduce dielectric irregularities. Optimized etching practices are evaluated using SEM, AFM, and optical profilometry to ensure pore depth and uniformity meet dielectric design specifications [34].

3.6.3. Mechanical and Thermal Characteristics

Performance during capacitor assembly is determined by the decisive characteristics of the mechanical properties of aluminum foil: tensile strength, ductility, and fatigue resistance. The parameters determine the ability of the foil to survive the winding, soldering and mechanical stresses during operation. Though the tensile strength of high-purity aluminum is usually lower, it is more formable, making it best used in tight windings used in capacitors. However, processing operations like the rolling and etching of the material introduce dislocation tangles and strain hardening that should be reduced by performing meticulously controlled annealing operations. Without such tempering, the foil will be very vulnerable to crack when winding [32]. It is then important to have an optimal mechanical balance: foils, when made too soft, will undergo deformation under the stress, and foils, when made too hard, will crack or delaminate at the interface with the dielectric layer.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

Thermally, aluminum foil is a heat sink and conductive copper, therefore, has a dual capability of conducting and dissipating Joule heat produced by charge-discharge. But, the difference in the coefficient of thermal expansion (CTE) between the foil and the dielectric substrate can cause mechanical stress in the thermal excursions. This disproportion can trigger delamination or microcrack development in the oxide layer, especially in a high-rate thermal cycling [33]. Moreover, prolonged exposure to high temperatures may hasten oxide hydration and rise leakage current particularly when microcracks permit fresh aluminum to be in contact with the electrolyte. As a resulting effect, cyclic-loading thermal fatigue testing has become a standard procedure in high-reliability capacitor design.

Mechanical integrity of the aluminum foil material, particularly post-processing, etching and anodization is critical in determining the long-term durability of the capacitor. Any weakening of foil strength as a result of residual stress or micro structural defects may result in early failure when the component is loaded with dynamic mechanical loads. The modern testing of fatigue resistance, thermal creep and dimensional stability is regularly conducted through finite element modeling alongside the experimental fatigability testing techniques like bend testing [36].

3.7. Production of Aluminum Electrolytic Capacitors

Electrolytic capacitors are glassy alkylation of aluminum manufacturing is a complex pattern of actions that require attention, quality assurance, and technology. Starting with the first steps of the material selection and the preparation of aluminum foil through the latter stages of the capacitor assembly and testing, every step is crucial in defining the electrical characteristics, structural stability, and performance of the capacitor (Figure 10).



(Source: https://www.goconqr.com/mindmap/11826618/aluminium-foil)

Figure 10. Aluminum process flowchart

3.7.1. Foil Preparation (Rolling, Annealing, Cleaning)

Aluminum foil preparation of electrolytic capacitors the purification of aluminum foil used in the electrolytic capacitor is started by the cold rolling of high-purity ingots of aluminum, usually more than 99.99. This rolling operation produces thin sheets of aluminum but enhances a specific grain orientation usually cube-textured which provides optimum dielectric development when anodizing is further involved in the process. It is important that all parts of the foil are uniform in terms of thickness, as irregularities in this process may cause anomalies in the dielectric and capacitance changes while using it [7]. The rolling is carried out under stringent mechanical strain and temperature conditions to attain the required mechanical properties and micro structural uniformity.

After rolling, the aluminum foil is subjected to intermediate and final annealing to eliminate stresses inside the foil caused in the process of deformation. It increases the strength of grains and recrystallization, which boosts mechanical formability, and dielectric reliability, which decreases the density of defects and favors adhesion of oxides. There are strict control of the recrystallization temperature and heating rate; a fast heating may lead to the inhomogeneous shape of the grain, whereas a slow heating may lead to a decrease in throughput without an appreciable increase in structural properties [32]. Annealing is also known to increase ductility, which means that the foil can withstand the process of winding and slitting involved in capacitor assembly and cannot be mechanically broken.

The last process in the preparation of foils is extensive chemical cleaning to eliminate surface oils, oxides and contaminants. It is usually cleaned with alkaline or acidic baths and rinsed with deionized water and passivated on the surface. This is necessary since the residual contaminants or disproportions of oxide may interfere with the later anodization or etching processes, which may result in electrical shorting or dielectric breakdown [38].

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

3.7.2. Surface Treatment and Anodization Process

Surface treatment of aluminum foil is aimed at enhancing surface area and making it active in formation of a stable layer of dielectric oxide. This is normally done with the aid of controlled electrochemical etching in the acid solutions like hydrochloric or nitric acid. The etching process forms a porous, tunnel-like structure of microstructure which increases the surface area and permits higher capacitance per physical volume. The parameters of the etching process like the density of current, temperature, and composition of the electrolyte are adjusted to achieve a balance between pore size, depth, and distribution [30]. The formation of dielectrics may be compromised by poorly etched surfaces that introduce sharp edges or skinny walls that may easily break.

The foil is then anodized with anodization being the electrochemical deposition of a dielectric layer of aluminum oxide. In this process, the foil of aluminum is dipped into a boric, phosphoric or sulfuric acid electrolyte and subjected to a DC voltage that is closely monitored. The thickness of the oxide coating formed is dependent on the applied voltage and is directly proportional to the voltage rating of the capacitor (Figure 11). A uniform barrier oxide with high dielectric strength and self-healing capacity is usually obtained by anodizing to form amorphous, compact Al_2O_3 [35]. It is a time dependent and temperature dependent process, which must be carefully controlled to avoid non-uniform growth or thermal cracking of the dielectric.



(Source: https://www.researchgate.net/figure/Porous-oxide-layer-formed-on-anodised-aluminium_fig2_226852281)

Figure 11. Cross-section diagram of aluminum oxide layer formation during anodization

A post-anodization sealing step can be used to enhance the dielectric performance and minimize residual stresses in the oxide. This is achieved by immersing the foil into hot deionized water or steam which moisturizes the outermost part of the oxide and transforms it into crystalline boehmite, and, in the process, diminishes the defect pathways and enhances dielectric stability. It is a sealed layer that prevents the ingress of moisture, and attack by electrolytes, which increases the life of the capacitor.

3.7.3. Electrolyte Composition and Soaking Process

In electrolytic capacitors made of aluminum, the electrolyte serves as an ionomer as well as a self-healing medium of the dielectric when used. It generally includes a solvent, like ethylene glycol or gamma -butyrolactone and dissolved with organic or inorganic acids e.g., boric acids, phosphoric acid or adipic acid as well as additives to stabilize pH and conductivity (Figure 12). The composition should be ionically mobile and thermally stable and should be compatible with the oxide film since hostile or excessively acidic solutions may damage the dielectric with time [39]. Corrosion inhibitors and viscosity modifiers are also added as advanced formulations to optimise wetting of the dielectric.

After the electrolyte is made, the electrolyte solution (aluminum foil assembly already rolled or stacked with a separator paper) is moistened in the electrolyte under vacuum or low pressure to allow complete impregnation. The soaking process should be timed to prevent inadequate penetration and excessive saturation that may affect the capacitor leakage current and capacitor formation of the dielectric. Vacuum soaking can also eliminate any trapped gases in the microporous structure of the etched foil, eliminating the formation of bubbles and uniform distribution of electrolytes on the dielectric surface [38]. The absorption behaviour of the electrolyte with the dielectric layer is important in long-term stability and it is actively researched in reliability tests.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577



(Source: https://www.physics-and-radio-electronics.com/electronic-devices-and-circuits/passive-components/capacitors/electrolyticcapacitor.html)

Figure 12. Diagram of capacitor assembly during soaking

The other aspect in the electrolyte process is that it affects capacitor performance under temperature and voltage stress. The oxide can be decomposed by electrolytes, dried or chemically attacked resulting in an increase in equivalent series resistance (ESR) or irreparable dielectric breakdown. Electrolytes are, therefore, subjected to accelerated aging to simulate their behaviour with longer periods of operation. Research and development in the field of solid-state or gel electrolyte carrying on to enhance thermal stability and leakage resistance is underway.

3.7.4. Packaging and Sealing

The physical structure of the capacitor is finally accomplished with packaging and sealing which provides the capacitor with environmental protection during service. The impregnated foil roll is then placed into an aluminum can or polymer casing and electrical leads are then welded or crimped to the foil terminals. The remaining electrolyte is then added and assembly is sealed with rubber gaskets, crimped lids or laser welding according to the product use and performance needs. It is recommended to properly seal to avoid evaporation of electrolytes and contamination and internal pressure build up, which have impacts on capacitance and dielectric behaviour with time.

A reasonable choice of sealing materials and architectural design is based on the operating environment expected. As an example, capacitors that will be used in the automotive or industrial market would have to be able to withstand large thermal variations and mechanical shock, which would require hermetic sealing or crimp joints reinforced with structure. On the other hand, consumer electronics general-purpose capacitors can be more parsimonious in sealing to reduce the manufacturing expense. The sealant material should also be chosen in such a way that it is chemically compatible with the electrolyte, and the dynamics of aging of elastomers in the conditions of thermal cycling [38].

Testing of quality assurance during the packaging stage includes leak testing, impedance, capacitance testing and pressure-stability. To emulate wear of a given operation, sealed capacitors are often exposed to such accelerated-life tests as high-temperature storage or ripple-current loading. At this point, failure is usually caused by leakage of electrolytes, tearing of the seal or poor weld adhesion. The latter is mitigated by automated sealing mechanisms and in-process diagnostics enhancing the measurement of torque, temperature, and fill level during the process of packaging.

3.8. Performance Characteristics of Aluminum Foil-Based Capacitors

3.8.1. Capacitance, ESR, and Leakage Current

The fundamental electrical property of an anodized aluminum oxide capacitors is capacitance, which is largely dominated by the surface area of the etched foil, dielectric layer thickness and dielectric constant of anodized aluminum oxide. The effective porosity induced during the etching process increases the foil working area that allows more charge to be amassed within small volumes. The anodized aluminum oxide brings to bear an energy-dense design in the capacitors, with a stable and self-healing dielectric of high breakdown strength. The amount of values of the capacitance is sensitive to the spacing and uniformity of dielectric, making the consistency of the oxide growth and the impregnation of the electrolyte imperative to the stability of the operation.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

Equivalent series resistance (ESR) is the internal resistance of the capacitor and directly affects power dissipation and ripplevoltage performance. Reduced ESR values would be desirable because they can be charged and discharged quickly and thermal buildup is reduced. The conductivity of the electrolyte, contact resistance at terminal joints, and foil microstructure determine ESR in aluminum electrolytic capacitors. According to the empirical research, it is possible to achieve a significant reduction in ESR with fine-pored etching using low-viscosity electrolytes without the need to degrade dielectric integrity [40]. High ESR is harmful in switching power supplies and inverter circuits where sudden load changes require rapid capacitor response.

Another important performance metric is leakage current that is a minute current flowing through the dielectric during operation. The leakage should be insignificant but defects in the oxide coat or chemical decay in the electrolyte may cause leakage in the long-run. High leakage currents introduce loss of energy and increase the probability of dielectric breakdown. Leakages are suppressed by the self-healing property of aluminum oxide, which reoxidizes small holes, but the self-healing process is not as efficient at high voltage or temperature [41].

3.8.2. Dielectric Strength and Reliability Metrics

Thickness and uniformity of anodized layer of aluminum oxide during the capacitor manufacturing is the major determinant of dielectric strength in aluminum-foil capacitors. An electrically charged dielectric that is well formed is capable of resisting electric fields up to almost 700 V/mm-1. This strength is directly proportional to the formation voltage in the anodization process; during thin-film electrolyte concentration and temperature must be carefully controlled to prevent the occurrence of dielectric weaknesses. Higher voltage rate capacitors will have to use a thicker oxide film, which reduces capacitance slightly, but increases stability [23]. Dielectric strength and performance are interrelated and this relationship involves trade-offs in terms of film thickness, pores and conductivity, which affect reliability.

The metrics of reliability used to describe aluminum electrolytic capacitors include operational life, thermal capabilities as well as mechanical shock tolerance. Life testing normally follows standards of IEC and adopts accelerated aging under high temperature and ripple-current conditions. Arrhenius model is frequently used to offer life prediction and assumptions under thermal stress, where doubling of life expectancy is assumed with every 10 o C of decreasing operating temperature. The lifespan of capacitors varies between 1,000 and more than 10,000 h depending on the design and use [42]. A loss of capacitance more than 20% indicated end-of-life, or an increment in ESR, or an increase in leakage current beyond recommended limits.

The voltage derating metric and ripple-current metrics are important ones when measuring the long-term reliability. When powered within their rated voltage especially when used in variable load set-ups, capacitors wear out faster. Ripple current causes internal heating which also affects the stability of electrolytes and durability of oxides. This means that performance characterization should include ripple-endurance curves and thermal-rise limits, in particular, that can be used in high-frequency switch-mode power supplies.

3.8.3. Effects of Temperature and Frequency

The temperature has a strong effect on all of the electrical parameters of aluminum electrolytic capacitors. Increase in temperature leads to increased ionic mobility in the electrolyte resulting in decreased ESR and temporarily higher capacitance. Although, prolonged exposure to high temperatures degrades the electrolyte by evaporation or chemical breakdown, which has the effect of increasing ESR and reducing capacitance with time. The loss of electrolytes also increases the chances of dielectric dry up and breaking even in high voltage rate units where oxides films are already stretched [23]. Capacitors should thus be derated to use in conditions beyond 85 o C or 105 o C to maintain design-life integrity.

Low temperatures are a unique challenge. In frozen or almost frozen electrolytes ionic conductivity is significantly reduced, resulting in an increase in ESR and a reduction in capacitance. This may hinder start-up performance in the outdoors or unheated conditions like automotive electronics. To address this, manufacturers tend to add antifreeze agents or to choose low-viscosity solvents, at the cost of long-term stability of electrolytes [43]. Another limitation is frequency response; beyond 10 -1 frequencies, capacitance drop across aluminum electrolytic capacitors is steep because of dielectric relaxation, high impedance in etched foil structures and thus these devices are inapplicable in high-frequency filtering where ceramic capacitors are preferred.

Temperature frequency stress can also act together to amplify the dislocation in thermal expansion between the aluminium base and dielectric layer, which promotes mechanical fatigue. It has been shown that capacitor integrity is especially detrimental to cyclic thermal loading accompanied by ripple frequencies in the 5-20 kHz frequency range, which leads to the rapid growth of ESR and accelerated aging [22].

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

3.8.4. Durability, Shelf-Life, and Degradation Modes

The life of aluminum foil-based capacitors Durability of aluminum foil-based capacitors includes the capacity to maintain electrical characteristics during continuous or discontinuous use during years. Durability determinants entail the strength of oxide film, rate of electrolyte evaporation, integrity of the seal and mechanical strength. The loss of water and solvent into the electrolyte because of imperfect seals causes drying out over time and therefore raises ESR and decreases the capacitance. Poor sealing is one of the most common reasons of premature failure in large can-type capacitors [44]. These issues are long-term durability achieved through proper storage conditions, such as cool and dry conditions and periodic reforming of idle capacitors.

Shelf-life is the duration of storage time that a capacitor can retain its performance without any major performance reduction. In the case of wet electrolytic capacitors, the shelf-life is normally lower than the operating life since the dielectric film is prone to degradation in the absence of applied voltage, which is referred to as depassivation. This causes high leakage current on reapplication of the voltage. One way to overcome this is to undertake the reformation process that entails the gradual increase of voltage in order to maintain the integrity of the oxides prior to deployment. Defense, aerospace, and industrial applications in stockpiles are particularly sensitive to shelf-life, as the components can be stored over years before being used [41].

The modes of degradation are electrolyte dry-out, seal leakage, internal corrosion and mechanical deformation. Such failures are usually progressive and can be identified by change in ESR and leakage current before failure occurs fully. Electrical impedance spectroscopy (EIS) and temperature-accelerated aging tests are modern methods of diagnostic tools used to predict the degradation trends. The failure mode of a capacitor is not usually explosive or violent, but more of a progressive one, where capacitance (and ESR) decreases, until the component is out of specification.

3.9. Technological Advancements

Design and operation design Aluminum electrolytic capacitors have continued to be improved to meet increasingly smaller, higher-efficiency, and longer-lived energy storage devices. With the modern electronics moving increasingly to embedded, flexible, and intelligent systems, capacitors no longer have to be made in the conventional wound foil configuration. To achieve these new requirements, engineers and researchers are investigating new materials and new formats. Other important advances are surface modification of aluminum at the nanoscale to increase surface area and dielectric, solid-state and polymer-based electrolytes to improve reliability, as well as flexible or printable designs that would be used in electronics of the next generation. Such developments are transforming the use of aluminum capacitors and they can now be used in new applications, including wearable devices and self-powered systems.

3.9.1. Use of Solid-State and Polymer Electrolytes

Traditional capacitors with liquid electrolytes have issues of leakages, evaporation and thermal instabilities. In response to these factors, new technologies have brought about polymer and solid-state electrolytes that are more stable and have a long service life. Polymer electrolytes produced using the polyethylene oxide or PVDF-HFP provide good ion mobility and chemical resistance without putting the chance of leakage. They are also used to achieve slimmer capacitor profiles that are suitable to a compact and portable device [45]

This method has been enhanced by solid-state electrolytes, which do not contain any fluid. Such systems can operate in large temperature spans, as low as −40°C to over 125°C, depending on chemical structure. They also have more positive interactions with dielectric materials and housing parts and minimize compatibility problems. They also resist moisture and vibration among other environmental stressors, which provide them with a competitive advantage over the normal wet-type capacitors, particularly in harsh environments [46]. Moreover, these materials make it easier to do miniaturized designs, because it can be coated by methods like spin coating, screen printing, or inkjet deposition. On the same note, solid-state electrolytes and polymer electrolytes are commonly supplemented by ionic liquids or inorganic nanoparticles to boost their electrical and mechanical characteristics. As an illustration, adding nanofillers including titanium dioxide or silicon dioxide to the polymer matrices, it is possible to raise dielectric strength and reduce ESR. This hybrid unites the mechanical flexibility of polymers and the utility of ceramic materials [47].

3.9.2. Development of Flexible and Printed Capacitors

Elastic capacitors are also required in electronics that will be required to be shaped to fit or move with some part of the body, including foldable screens, med wearables and soft robotics. Conventional aluminum electrolytic capacitors are hard, although recent advances in the manufacture of materials have resulted in designs that can be bent or flexed without impairment. It is done through the application of stretchable aluminum substrates and gel-like or elastomeric electrolytes tolerant to mechanical deformation [48].

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

With printing technology, these possibilities have been further increased. It is now possible to print the components of the capacitors directly onto the flexible films or fabrics with the help of conductive inks, dielectric pastes and gel electrolytes. These printed structures are possible based on the screen printing, inkjet and gravure methodology, lowering manufacturing costs and enabling a direct integration into lightweight and disposable electronics [49]. They can be used in powering wearable medical patches and soft sensors in environmental monitors.

Pressed capacitors can be used as well with a custom shape and design. Rather than having to use the conventional cylindrical or rectangular shapes, the artist can build a spiral, grid or thin-film design that is more efficient in using space across irregular surfaces. A problem is with adhesion between the printed layers, especially between aluminum and dielectric. In order to counter this, methods are being discussed to adhere to plasma surface and use nanoscale primers in order to enhance bond and stability of layers.

3.9.3. Integration in Smart Devices and Wearables

The desire to have ubiquitous, always-on consumer electronics has exacerbated the need to have energy elements that can easily be integrated with sensors, processors and communication modules. Structural miniaturization and functional compatibility with flexible substrates have seen aluminum-based capacitors meet this challenge. Recent studies highlight the development of capacitors into smart textiles, patches and implantable gadgets, reliability in a physical stress environment is equally vital as the power output of the capacitors [50].

Smartwatches, hearing aids, medical diagnostics and IoT sensors require capacitors which are not only small but also withstanding to bending back and forth, being exposed to sweat or water and long-term skin contact. It has also been found especially useful in solid electrolyte polymer-coated aluminum capacitors, which are both long lasting and with very little outgassing. They are now being combined with other flexible circuits and energy sources, like organic photovoltaics and thermoelectric harvesters, to form energy-independent systems [46]

In addition to consumer uses, flexible capacitors are being integrated into flight suits, autonomous drones, and soft robotics, where the weight and profile of flight-suits, along with the environmental friendliness is the mission requirement. Capacitor arrays mounted on flexible substrates do not only save on space but also improve energy density per unit volume, hence, guaranteeing long operation time and increased system redundancy. More sophisticated material, such as graphene-based foils, ultra-thin ceramic dielectrics, etc., are being explored to expand the limits of what these embedded systems may be able to accomplish in the real world [51].

3.10. Applications of Aluminum Electrolytic Capacitors

The application of aluminum electrolytic capacitors has been used over a wide range of electronic systems due to their large capacitance, fairly small size and affordability. The characteristics make them applicable to consumer and industrial technologies and include power supplies, audio systems, control units, and automotive electronics.

3.10.1. High-Power and High-Frequency Circuits

Aluminum electrolytic capacitors are essential in energy buffering, voltage regulation and signal filtering in high-power circuits and high-frequency circuits. They are commonly used in DC-link sections, input and output filters and in energy storage stages of power converting electronic devices. They can easily handle high ripple currents and moderate voltage surges and have a relatively small footprint, which makes them suitable in inverters, converters, and motor drive systems [52]. In these capacitors, the capacitor foil used is an etched and anodized to expose a higher surface area, thus, allowing more energy to be stored in the same device volume, and maintaining one of the series resistance (ESR) to reasonable power operational limits.

The capacitors can be affected by higher frequencies causing higher impedance and phase lag that can limit the effectiveness of the capacitors at frequencies above 20 kHz. However, developments made in the electrolyte chemistry and foil structure have increased the frequency range. In many of the designs, ceramic or film capacitors have been used together with aluminum electrolytic to provide bulk energy storage and fast transient response [53]. The aluminum unit is used in such architectures to meet the requirements of long-term energy, and the supporting components are used to stabilize the high-speed changes of voltage. The thermal performance remains a very important factor in high frequency systems; large ripple currents may cause internal heating, which increases a faster breakdown of the electrolyte. To reduce this, producers have come up with high temperature electrolytes and casings which increase heat dissipation. The location of the capacitor in the system is also important especially around switching components with electromagnetic interferences and parasitic inductance that may reduce general efficiency and reliability.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

3.10.2. Renewable Energy and Power Electronics

The Aluminum electrolytic capacitors are widely applied in renewable energy sources such as solar inverter, wind turbine controller and battery management unit. They are utilized to stabilize DC bus voltages, minimise ripple, and store energy during short time variations in load. These capacitors in photovoltaic systems smooth the output of DC to DC converters and before the output is delivered to grid connected inverters. They offer reliable modular power system options due to their ability to manage surge loads and are economical to operate [54].

Voltage discontinuities due to varying wind speeds may create instability in wind energy applications. This output is stabilized with the help of aluminum capacitors, which ensure that the electronics downstream are not subjected to unnecessary pressure. These capacitors can withstand thermal cycling, mechanical vibration, and humid outdoor conditions that are often experienced in renewable installations [30]. In order to be reliable, real time monitoring methods like impedance spectroscopy are also widely used to ensure that they can see the degradation in their infancy so that the operators can schedule maintenance before failure can take place.

Where short-term energy delivery is needed and also to level power over the grid, in the case of a hybrid energy storage system that combines batteries and supercapacitors, aluminum electrolytic capacitors are used. They are especially helpful in the voltage-balancing devices, power conditioning systems, and backup modules in the case of outages that require capacitors that have a strong tendency to tolerate ripple-current and very stable dielectric behavior during prolonged operation.

3.10.3. Automotive Systems (EVs and Hybrids)

The shift to electric and hybrid cars has increased the need in capacitors that can resist harsh operating conditions and handle fast changes in energy. Aluminum electrolytic capacitors are mainly applied in onboard chargers, DC-DC converters, motor controllers as well as auxiliary power units in automotive powertrains. They can buffer voltage, regenerative braking energy, and smooth inverter outputs, making them impossible to omit in traction drive systems [1].

Capacitors in DC-link of inverter-based electric vehicles will experience extreme temperatures, vibration as well as quick thermal changing. Manufacturers address such stresses by using high temperature electrolyte formulations and reinforced aluminum cans, and vibration resistant mechanical mounts. Retention of capacitance with time is the most important, and aging is accompanied by increased ESR and lower energy efficiency especially in high-load operation [55]. Capacitor arrays are used to provide fault tolerance and higher ripple current limits, as well, are commonly made in parallel to allow physical size to increase linearly with capacity requirement. Hybrid electric cars also take advantage of capacitors in idle-stop systems, start have ignition, and energy recovery sub-systems. Self-healing dielectrics and solid-state designs have been developed to meet the high cycle demands of these components and lower the cost of maintenance and increase service life. Capacitors are also used in the reduction of EMI and powerline noise cancellation, which enhance signal stability throughout vehicular communication networks.

3.10.4. Consumer Electronics and IoT Devices

Evidently, in consumer electronics, aluminum electrolytic capacitors still form a viable option in power supply smoothing, power decoupling, and power filtering. They are ubiquitous in AC-DC adapters, LCD backlight circuits, audio amplifiers, power units in small appliances. A combination of cost-effectiveness, accessibility, and the ability to offer high capacitance in compact spatial packages makes these elements essential in the electronics gadgets of the mass-market [56]. In applications like televisions, gaming consoles and set-top boxes, these capacitors are used to stabilize the voltage and reduce electromagnetic noise along the power lines.

Since the search towards smaller form factors and increased energy-efficiency in consumer devices has been in progress, capacitor design has been following suit. Smartphones, tablets and wearable technologies are now equipped with miniaturized aluminum electrolytic capacitors with high volumetric efficiency and low equivalent series resistance (ESR). Advances in solidpolymer electrolytes have now made it possible to make ultra-thin capacitors, which maintain a stable operation even as size reduces [57]. These elements are often put on flexible circuit boards or are placed near system-on-a-chip modules to reduce the inductive losses and to further develop the efficiency of power delivery.

Additional difficulties in the Internet of Things (IoT) machines include intermittent power usage, irregular activity periods, and autonomous functionality. In such systems, aluminum electrolytic capacitors act as transient buffering sources of energy in short spikes of power consumption (wireless communication, sensor activation, or data processing). They are also used in providing short pulses of energy in RF energy collection and low power sensing projects. As a result, dependency on primary batteries is reduced, and thus devices can become independent by using the harvested energy.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

4. Conclusion

Aluminum foil capacitors are also an important element in contemporary electronics; although they are everywhere, they are at the edge of what they can do. The key short-coming is due to the dielectric, Al2O3 whose operation, though satisfactory over decades, is no longer in step with the increased energy density and reliability requirements of modern systems. It is not just an academic deficit; it is now a practical limit. Here, calcium zirconate is not a fringe benefit but an option, a marginal innovation. It does not purport to make irrational extrapolations but rather makes a wise addition: high dielectric constant, excellent thermal stability, and durability in extreme operating scenarios. This kind of balanced improvement is important. Many high-k materials have been found to be attractive on paper but fail miserably once faced with the complexity of processing, cost or long-term stability considerations. It is worth noting that the currently existing manufacturing ecosystem of the aluminum electrolytic capacitors does not necessitate a complete overhaul. This review has shown that incorporation of calcium zirconate into the existing production lines can be easily completed by careful management of surface treatment, anodization, and dielectric integration. This is important since in many cases scalability can be the difference between a material making it out of the laboratory into the market. Calcium zirconate in a sense is a plausible, upwardly moving trend and not a disruptive threat. It correlates with the changing energy storage requirements of electric cars, renewable infrastructure, and miniaturized electronics. The existing difficulty is thus not in confirming its validity but one of demonstrating long-term reliability, cost-effectiveness and consistency in scale of process, which future research should focus on.

Author Contributions

All authors have equal contributions to the paper. All the authors have read and approved the final manuscript.

Funding

No funding support was received.

Declaration of Conflicting Interests

The author declared no potential conflicts of interest with respect to the research, authorship, and/ or publication of this article.

Data Availability

The datasets generated during and/ or analysed during the current study are available from the corresponding author on reasonable request.

Declaration on AI Use

The authors declare that no artificial intelligence (AI) or AI-assisted tools were used in the preparation of this manuscript.

References

[1] R. Vanaraj, B. Arumugam, G. Mayakrishnan, and S. Kim, "Advancements in Metal-Ion Capacitors : Bridging Energy and Power Density for Next-Generation Energy Storage," *Energies*, vol. 18, pp. 1–27, 2025, doi: https://doi.org/10.3390/en18051253.

[2] B. Fan *et al.*, "Dielectric materials for high-temperature capacitors," *Inst. Eng. Technol.*, vol. 1, no. 1, pp. 32–40, 2018, doi: 10.1049/iet-nde.2018.0002.

[3] H. Wang *et al.*, "High thermal conductive composite with low dielectric constant and dielectric loss accomplished through flower-like Al 2 O 3 coated BNNs for advanced circuit substrate applications," *Compos. Sci. Technol.*, vol. 216, no. September, p. 109048, 2021, doi: 10.1016/j.compscitech.2021.109048.

[4] F. Palumbo *et al.*, "A Review on Dielectric Breakdown in Thin Dielectrics : Silicon Dioxide , High- k , and Layered Dielectrics," *Adv. Funct. Mater.*, vol. 1900657, pp. 1–26, 2019, doi: 10.1002/adfm.201900657.

[5] H. Liu, B. Du, M. Xiao, Z. Ran, and Y. Ma, "Dielectric Properties of Polymer Films in Strong Electromagnetic Field for Energy Storage Capacitor," *IEEE Trans. Dielectr. Electr. Insul.*, vol. 29, no. 5, pp. 1745–1753, 2022, doi: 10.1109/TDEI.2022.3188588.

[6] C. Medina, C. R. M. Ana, and G. González, "Transmission Grids to Foster High Penetration of Large-Scale Variable Renewable Energy Sources – A Review of Challenges, Problems, and Solutions," *Int. J. Renew. ENERGY Res.*, vol. 12, no. 1, 2022.

[7] W. Liu, X. Sun, X. Yan, Y. Gao, X. Zhang, and K. Wang, "Review of Energy Storage Capacitor Technology," *Battrieries*, vol. 10, no. 8, 2024, doi: https://doi.org/10.3390/batteries10080271.

[8] P. Sharma and T. S. Bhatti, "A review on electrochemical double-layer capacitors," *Energy Convers. Manag.*, vol. 51, no. 12, pp. 2901–2912, 2010, doi: 10.1016/j.enconman.2010.06.031.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

[9] Y. Kumar, S. Rawal, B. Joshi, and S. A. Hashmi, "Background, fundamental understanding and progress in electrochemical capacitors," *J. Solid State Electrochem.*, vol. 23, pp. 667–692, 2019, doi: https://doi.org/10.1007/s10008-018-4160-3.

[10] J. Tahalyani, M. J. Akhtar, J. Cherusseri, and K. K. Kar, "Characteristics of Capacitor: Fundamental Aspects," *Springer Ser. Mater. Sci.*, vol. 300, 2020, doi: https://doi.org/10.1007/978-3-030-43009-2_1.

[11] F. Lo Presti, A. L. Pellegrino, and G. Malandrino, "Metal-Organic Chemical Vapor Deposition of Oxide Perovskite Films : A Facile Route to Complex Functional Systems," *Adv. Mater. Interfaces*, vol. 9, pp. 1–23, 2022, doi: 10.1002/admi.202102501.

[12] A. O. Akanwa *et al.*, "Effects of Climatic Risks on Soil Erosion/Desertification in Southern and Northern Nigeria Using GIS/Remote Sensing Analysis," *Clim. Cris. Adapt. Approaches Sustain.*, pp. 151–170, 2023, doi: https://doi.org/10.1007/978-3-031-44397-8_9.

[13] Anyakora *et al.*, "PROSPECTS AND CHALLENGES OF ADOPTING GREEN MAINTENANCE APPROACH IN," *Proc. FESCON*, vol. 5, no. 1, pp. 244–260, 2025, doi: https://ajer.org.ng/index.php/fescon-proceeedings/.

[14] C. P. Oramah and T. A. Ngwu, "Addressing the Impact of Complex English Use in Communicating Climate Change in Nigerian Communities Through Contextual Understanding," *Climate*, vol. 13, pp. 1–18, 2025, doi: https://doi.org/10.3390/cli13030056.

[15] C. N. Odimegwu and M. I. Anyakora, "LAND VALUE CAPTURE THROUGH LAND BASED TAXATION : FOR SUSTAINABLE INFRASTRUCTURE FINANCE IN ANAMBRA STATE ," *African J. Environ. Res.*, vol. 4, no. 1, pp. 121–138, 2023, doi: http://ajer.coou.edu.ng/index.php/journa.

[16] U. F. Ikechukwu and C. N. Odimegwu, "Implications of COVID – 19 Outbreak on the Construction and Property Development Sector in the South-East Nigeria," *J. Sci. Res. Reports*, vol. 27, no. 2, pp. 1–9, 2021, doi: 10.9734/JSRR/2021/v27i230354.

[17] F. N. Mbuba, C. Chukwueloka, and Chukwurah, "The Protuberance of Government Autonomy and Service Delivery in Anambra State," *Available SSRN 4187191*, 2022, doi: http://dx.doi.org/10.2139/ssrn.4187191.

[18] B. F. N. Mbuba, "Organizational Conflict and Business Growth: An Appraisal," *J. Public Adm.*, vol. 1, no. 2, 2016.

[19] F. N. Mbuba, "Federal character principle and Nigerian federalism: an overview an overview," *J. Soc. Sci. Public Policy*, vol. 13, no. 1, pp. 17–39, 2021.

[20] F. N. Mbuba, "Public Servants and Code of Conduct in Nigeria: A Study of Anambra State 2010-2015," *J. Soc. Sci. Public Policy*, vol. 10, no. 3, pp. 104–149, 2018.

[21] C. O. Ike, F. N. Mbuba, and F. Nwot, "Federal Government Housing Policy and Building Collapse in Anambra State: A Study of Awka Metropolis," *Available SSRN 3835073.*, 2021.

[22] B. Wang, J. Meng, and P. Zhao, "Aging Condition Monitoring for Aluminum Electrolytic Capacitor in Variable Speed Drives," *IEEE Trans. Power Electron.*, vol. 37, no. 4, pp. 4564–4574, 2021, doi: 10.1109/TPEL.2021.3121813.

[23] G. He, X. Li, H. Luo, D. Zhang, and S. org/10. 1002/adma. 20241956. Zhang, "The Large-Scale Manufacturing of Polymer Dielectric Capacitors: Advancements and Challenges," *Adv. Mater.*, vol. 2419563., 2025, doi: https://doi.org/10.1002/adma.202419563.

[24] M. Mirzaeian *et al.*, "Electrode and electrolyte materials for electrochemical capacitors," *Int. J. Hydrogen Energy*, vol. 42, no. 40, pp. 25565–25587, 2017, doi: 10.1016/j.ijhydene.2017.04.241.

[25] F. Palumbo *et al.*, "A review on dielectric breakdown in thin dielectrics: silicon dioxide, high-k, and layered dielectrics," *Adv. Funct. Mater.*, vol. 30, no. 18, p. p.1900657., 2020.

[26] X. Sun, Y. Qiao, Y. Li, C. Cao, and X. Guo, "Effect of thermal stress on the life of DC link capacitors for smart grid," *Sci. Rep.*, vol. 15, pp. 1–12, 2025, doi: https://doi.org/10.1038/s41598-025-88522-2.

[27] B. I. Okoli *et al.*, "Characterization of Nigerian Zircon Sand and Its Suitability for Different Industrial Applications," *minerals*, vol. 13, p. 711, 2023, doi: https://doi.org/ 10.3390/min13060711.

[28] D. Devoe *et al.*, "Peer Support for Youth with Mental Health Concerns : A Scoping Review," *Authorea Prepr.*, pp. 1–15, 2024.

[29] S. Pattipaka, Y. Lim, Y. H. Son, Y. M. Bae, M. Peddigari, and G.-T. Hwang, "Ceramic-Based Dielectric Materials for Energy Storage Capacitor Applications," *Materials (Basel).*, vol. 17, pp. 1–26, 2024, doi: https://doi.org/10.3390/ma17102277.

[30] C. Zhang, Y. Zheng, H. Huang, Z. Liu, and J. Jing, "Environmental impact assessment of aluminum electrolytic capacitors in a product family from the manufacturer ' s perspective," *Int. J. Life Cycle Assess.*, vol. 28, no. 1, pp. 80–94, 2023, doi: 10.1007/s11367-022-02117-x.

[31] T. Pandolfo, V. Ruiz, and S. Sivakkumar, "General properties of electrochemical capacitors," *Mater. Syst. Appl.*, 2013, doi: https://app.scholarai.io/paper?paper_id=DOI:10.1002/9783527646661#page=96.

[32] H. Wang, J. Ma, Y. Yang, and Q. Wang, "A Review of System-in-Package Technologies : Application and Reliability of Advanced Packaging," *micromachines*, vol. 14, p. 1149, 2023, doi: https://doi.org/ 10.3390/mi14061149.

[33] Q. Zhang and L. Cao, "Investigation of laser sintering process parameters for anode foils in aluminium electrolytic capacitors considering temperature distribution Investigation of laser sintering process parameters for anode foils in aluminium electrolytic capacitors consider," *Mater. Res. Express*, vol. 11, p. 116515, 2024, doi:

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

https://doi.org/10.1088/2053-1591/ad8f19.

[34] N. Osawa, "Etching Behavior and Dielectric Film Formation on Aluminum Foil Stocks for Electrolytic Capacitors : A Review," *Mater. Trans.*, vol. 65, no. 8, pp. 825–836, 2024, doi: 10.2320/matertrans.MT-L2024006.

[35] S. Pan, L. Liang, B. Lu, and H. Li, "Microstructure evolution for oxide fi lm of anodic aluminum foil used in high voltage electrolytic capacitor," *J. Alloys Compd.*, vol. 823, p. 153795, 2020, doi: 10.1016/j.jallcom.2020.153795.

[36] D. Jeanvoine, "Tailoring the Etchability of Aluminium Foil by Laser Interference Metallurgy : Control of Pit Initiation Sites for High-Voltage Aluminium Capacitor Applications," *Saarl. Univ.*, 2010, doi: https://publikationen.sulb.uni-saarland.de/bitstream/20.500.11880/22782/1/Dissertation_DAlessandria.pdf.

[37] X. Du, B. Lin, B. Li, T. Feng, S. Mao, and Y. Xu, "Surface Modification of Al Foils for Aluminum Electrolytic Capacitor," *Adv. Funct. Mater.*, vol. 27, no. 13, 2017, doi: 10.1002/adfm.201606042.

[38] C. Lee *et al.*, "Effect of Anodization Treatment on the Thickness , Hardness , and Microstructural Characterization of Anodic Aluminum Oxide Film on AA 6061 and Critical Patent Analysis," *J. Mater. Eng. Perform.*, vol. 31, no. 1, pp. 667–681, 2022, doi: 10.1007/s11665-021-06205-1.

[39] J. S. Santos *et al.*, "The Use of Anodic Oxides in Practical and Sustainable Devices for Energy Conversion and Storage," *Materials (Basel).*, vol. 14, p. 383, 2021, doi: https://doi. org/10.3390/ma14020383 Received:

[40] X. Guo *et al.*, "Holistic Processing of Sawdust to Enable Sustainable Hybrid Li-Ion Capacitors," *JOM*, vol. 76, no. 7, pp. 3557–3566, 2024, doi: 10.1007/s11837-024-06542-1.

[41] G. Yu, X. Xie, L. Pan, Z. Bao, and Y. Cui, "Hybrid nanostructured materials for high-performance electrochemical capacitors," *Nano Energy*, vol. 2, no. 2, pp. 213–234, 2013, doi: 10.1016/j.nanoen.2012.10.006.

[42] A. A. Mirza, I. U. Nutkani, C. A. Teixeira, and B. P. McGrath, "A Sensorless Grid Voltage Estimation Scheme for a Single-phase Voltage Source Inverter," *2023 11th Int. Conf. Power Electron. ECCE Asia*, pp. 792–798, 2025, doi: https://0.23919/ICPE2023-ECCEAsia54778.2023.10213876.

[43] A. Yusuf, L. Prasetyani, D. Sudiana, A. S. Tamsir, and S. H. Sudibyo, "Design of capacitive sensor, measurement and data acquisition system of ECVT," *2017 Int. Conf. Electr. Eng. Informatics*, pp. 40–44, 2017, doi: 10.1109/ICELTICS.2017.8253245.

[44] F. Blaabjerg, H. Wang, and D. A. Nielsen, "Microelectronics Reliability Degradation testing and failure analysis of DC fi lm capacitors under high humidity conditions," *Microelectron. Reliab.*, vol. 55, no. 9, pp. 2007–2011, 2015, doi: 10.1016/j.microrel.2015.06.011.

[45] C. Chelaru and R. M. Aileni, "CAPACITORS – ADVANCED MATERIALS – REVIEW," *Sciendo*, vol. 39, pp. 35–40, doi: 10.2478/9788367405386-005.

[46] C. Rokaya, *Printed Energy Storage for Energy Autonomous Flexible Electronics*. Finland: PunaMusta Oy – Yliopistopaino.

[47] A. Rajpoot and N. Banik, "Material Science Research India A Review on the Recent Development on Polymer Nanocomposite for Energy Storage Application," *Mater. Sci. Res. India*, vol. 20, 2023, doi: http://dx.doi.org/10.13005/msri.20.special-issue1.02.

[48] R. B. Mishra, N. El-Atab, A. M. Hussain, and M. M. Hussain, "Recent Progress on Flexible Capacitive Pressure Sensors: From Design and Materials to Applications," *Adv. Mater. Technol.*, vol. 6, no. 4, p. 2001023, 2021, doi: https://doi.org/10.1002/admt.202001023.

[49] S. Xu and W. Wu, "Ink-Based Additive Nanomanufacturing of Functional Materials for Human-Integrated Smart Wearables," *Adv. Intell. Syst.*, vol. 2, p. 2000117, 2020, doi: 10.1002/aisy.202000117.

[50] V. Sakthivelpathi, T. Li, Z. Qian, C. Lee, and Z. Taylor, "Sensors and Actuators : A . Physical Advancements and applications of micro and nanostructured capacitive sensors : A review," *Sensors Actuators A. Phys.*, vol. 377, no. July, p. 115701, 2024, doi: 10.1016/j.sna.2024.115701.

[51] V. K. Khanna, *Flexible Electronics , Volume 3*, vol. 3. IOP Publishing, 2019. doi: https://doi.org/10.1088/2053-2563/ab0d19.

[52] J. Schnack, S. Brückner, H. Süncksen, U. Schümann, and R. Mallwitz, "Analysis and Optimization of Electrolytic Capacitor Technology for High-Frequency Integrated Inverter," *IEEE*, vol. 11, no. 6, 2021, doi: 10.1109/TCPMT.2021.3084371.

[53] H. Zhang, H. Tan, and M. A. Marwat, "Applications and Prospects of Dielectric Materials for Capacitive Energy Storage," *Dielectr. Mater. Capacit. Energy Storage*, p. 39, 2024.

[54] M. W. Ahmad, N. Agarwal, P. N. Kumar, and S. Anand, "Low-Frequency Impedance Monitoring and Corresponding Failure Criteria for Aluminum Electrolytic Capacitors," *IEEE Trans. Ind. Electron.*, vol. 64, no. 7, pp. 5657–5666, 2017, doi: 10.1109/TIE.2017.2674598.

[55] S. Jeong, A. B. Kareem, S. Song, and J. Hur, "ANN-Based Reliability Enhancement of SMPS Aluminum Electrolytic Capacitors in Cold Environments," *Energies*, vol. 16, no. 6096, pp. 1–16, 2023, doi: https://doi.org/10.3390/en16166096.

[56] J. Both, "The modern era of aluminum electrolytic capacitors," *IEEE Electr. Insul. Mag.*, vol. 31, no. 4, pp. 24–34, 2015, doi: 10.1109/MEI.2015.7126071.

[57] K. Paul, "Development of electromagnetic vibration energy harvesters as powering solution for IoT based

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577

applications," *Univ. Coll. Cork, Dr. thesis*, 2022, doi: https://cora.ucc.ie/bitstreams/5e0b38f9-b450-407d-bc23-8765323ac40f/download.

© 2026 The Author(s)
This work is licensed under a Creative Commons Attribution-ShareAlike 4.0 International License
ISSN: 3110-1577